



Stucco Selector Guide

Stucco Products

One Coat Fiberglass Reinforced Stucco
(No. 1200-80)



One Coat Fiberglass Reinforced Concentrated
(No. 1216-93)



Base Coat
(No. 1139-80)



Base Coat with Water-Stop
(No. 1139-89)



QUIKWALL® Surface Bonding Cement
(No. 1230 & 1231)



Finish Coat
(No. 1201-80)



	Fiberglass Reinforced One Coat w/Sand	Fiberglass Reinforced One Coat-Add Sand	Scratch & Brown Coat	Water Resistant Scratch & Brown Coat	Dry Stack Block Stucco	Color & Texture Coat
Application	Scratch Coat: N/A Brown Coat: 3/8" - 5/8" • Trowel or spray apply	Scratch Coat: N/A Brown Coat: 3/8" - 5/8" • Apply one coat • Trowel or spray apply	Scratch Coat: 3/8" Brown Coat: 3/8" • Trowel or spray apply • Apply directly to masonry walls in 2-coat application	Scratch Coat: 3/8" Brown Coat: 3/8" • Trowel or spray apply • Apply directly to masonry walls in 2-coat application	Single Coat: 1/8" - 1/4" • Use for dry stack block construction -eliminates need for mortar	Finish Coat: 1/8"
Attributes	<ul style="list-style-type: none"> Alkali resistant fiberglass reinforced 1 hour fire rating over EPS foam & OSB and EPS foam & plywood Factory pre-blended mix 	<ul style="list-style-type: none"> Alkali resistant fiberglass reinforced 1 hour fire rating over EPS foam & OSB and EPS foam & plywood Add 180 to 250 lb. (81.7-113.4 kg) of plaster sand 	<ul style="list-style-type: none"> Use for scratch & brown coat in a 3-coat application Exceeds performance of ASTM C 926 	<ul style="list-style-type: none"> Water resistant against wind driven rain Use for scratch & brown coat in a 5-coat application Exceeds performance of ASTM C 926 	<ul style="list-style-type: none"> Alkali resistant fiberglass reinforced 1-coat application provides strength & texture finish Waterproofed coating Colors: gray & white 	<ul style="list-style-type: none"> Color & texture coat Integral color can be added to mix Factory pre-blended Colors: gray & white
Coverage (per bag)	25 f ² at 3/8" (2.3 M ² at 8 mm) 20 f ² at 1/2" (1.9 M ² at 12 mm)	25 f ² at 3/8" (2.3 M ² at 8 mm) 20 f ² at 1/2" (1.9 M ² at 12 mm)	25 f ² at 3/8" (2.3 M ² at 8 mm)	25 f ² at 3/8" (2.3 M ² at 8 mm)	50 f ² at 1/8" (4.6 M ² at 3 mm)	70 f ² at 1/8" (6.5 M ² at 3 mm)
Application						
Scratch Coat	Not necessary	Not necessary	•	•		
Brown Coat	•	•	•	•		
Apply Directly to Masonry Walls			•	•	•	
Finish Coating					•	•
Dry Stack Walls					•	
Apply Directly to Concrete			• w/ Acrylic Fortifier (No. 8610)	• w/ Acrylic Fortifier (No. 8610)	• w/ Acrylic Fortifier (No. 8610)	
Waterproof Masonry Walls					• w/ Acrylic Fortifier (No. 8610)	

For SPEC DATA and Guide Specification documents on all our Commercial Grade products, please visit our "On the Job" section at www.quikrete.com